

TEST REPORT

No. : SHCCM160200600

Date : Mar. 09, 2016


Page: 1 of 1

The following sample(s) was/ were submitted and identified on behalf of the client as:

Sample Name : PET ACOUSTIC PANEL
Sample Number : SHCCM160200600
Test Required : Sound absorption coefficient
Test Method : ISO 354:2003
Product specification : 2440x1220x12mm
Date of Receipt : Feb. 23, 2016
Test Period : Feb. 23, 2016 to Mar. 09, 2016
Test result(s) : For further details, please refer to the following page(s)

***** To be continued *****

Signed for SGS-CSTC Standards
Technical Services (Shanghai) Co., Ltd.



Erin Huang
Authorized signatory



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.
Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN Doccheck@sgs.com
No. 69, Block 1159, East Kang Qiao Road, Pudong District, Shanghai, China. 201319 t (86-21) 61196300 f (86-21) 61191853/68183920 www.sgs.com.cn
中国·上海·浦东康桥东路1159弄69号 邮编: 201319 t (86-21) 61196300 f (86-21) 61191853/68183920 e sgs.china@sgs.com

Member of the SGS Group (SGS SA)

Vibraplast AG

Wittenwilerstrasse 25, 8355 Aadorf

+41 (0) 52 368 00 50 / info@vibraplast.ch / www.vibraplast.ch



TEST REPORT

No. : SHCCM160200600

Date : Mar. 09, 2016

Page: 2 of 2

I. Test method

EN ISO 354:2003 Acoustics-Measurement of sound absorption in a reverberation room

II. Sample Details

Sample Specification	2440mmx1220mmx12mm
----------------------	--------------------

Remark: the above details are provided by client for reference.

III. Test condition

Ambient temperature	15°C	Relative humidity	67%
Volume reverberation room	273m ³	Test area	10.08m ² , with back airspace of 200 mm

IV. Test result

Noise Reduction Coefficient: NRC=0.85

***** To be continued*****

Vibraplast AG

Wittenwilerstrasse 25, 8355 Aadorf

+41 (0) 52 368 00 50 / info@vibraplast.ch / www.vibraplast.ch


TEST REPORT

No. : SHCCM160200600

Date : Mar. 09, 2016

Page: 3 of 2

f Hz	α_s
50	/
63	/
80	/
100	0.62
125	0.69
160	0.71
200	0.91
250	0.92
315	0.87
400	1.08
500	0.96
630	0.84
800	0.74
1000	0.76
1250	0.88
1600	0.84
2000	0.79
2500	0.76
3150	0.79
4000	0.74
5000	0.76
NRC	0.85



Note: The test was carried out by external laboratory assessed as competent.

Statement: Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

***** To be continued*****

Vibraplast AG

Wittenwilerstrasse 25, 8355 Aadorf

+41 (0) 52 368 00 50 / info@vibraplast.ch / www.vibraplast.ch



TEST REPORT

No. : SHCCM160200600

Date : Mar. 09, 2016

Page: 4 of 2

Sample photo:



***** End of report *****